



Typical Properties of

Tefzel® ETFE

Ethylenetetrafluoroethylene

Process: Extruded

Property	Test Method	Unit	Value
Specific Gravity	D792	--	1.74
Tensile Strength	D638	psi	6,500
Tensile Modulus	D638	psi	217,000
Elongation	D638	%	300
Flexural Strength	D790	psi	N / A
Flexural Modulus	D790	psi	180,000
Compressive Strength	D695	psi	N / A
Compressive Modulus	D695	psi	N / A
Hardness, Rockwell	D785	--	N / A
Hardness Durometer	--	--	D75
Izod Impact (notched)	D256	ft. lb of notch	No Break
Coeff. of Friction (Dynamic)	--	dry v.s steel	0.23
Coeff. of Linear Therm. Expan.	E831/ D696	in./in./°F	5.2×10^{-5}
Continuous Use Temperature	--	°F	300
Heat Deflection Temperature	D648	°F	160
Glass Transition Temperature	D3418	°F	N / A
Melting Point	D3418	°F	512
Thermal Conductivity	E1530-11	BTU in/hr ft ² °F	N / A
Dielectric Strength	D149	Volts/mil	450
Surface Resistivity	EOS/ESD 511.11	ohm/square	$>10^{16}$
Flammability	UL94	--	V-0
Water Absorption, 24 hrs.	D570	% by weight	0.03
Water Absorption, Saturation	D570	% by weight	0.03
Limiting PV (4:1 Safety Factor)	--	--	N / A
K-Factor	--	--	N / A
FDA Compliance	--	--	No

Note: The data provided is for reference purposes only. Additional testing may be required for design specifications or quality control.
All values at 73 F unless otherwise stated.